



Schaepman's Lakfabrieken b.v.
Gildestraat 9
8263 AH Kampen
Nederland

(kenmerk
K025304)

TEST REPORT

DATE : 25-07-2016

CLIENT ID : 254215
CLIENT : Power-Packer Europa B.V.
PRODUCT : Belticryl 2 comp.lak RAL9005 eigl
PRODUCTCODE : C4P000185
YOUR PRODUCTCODE :
BATCHNO. : KR52876
RELEASE DATE :

klëntartikel nummer ontbreekt.

TEST DESCRIPTION	TEST	STANDARD	UNIT	POS.	NEG.
				TOL.	TOL.
Potlife, after 2 Hrs	19	< 40	Sec/DC4		
Specific weight acc. ISO2811-2	1.21	1.21	gr/cm3	0.05	0.04
Viscosity, DIN Cup 4 acc. ISO2431	66	65	Sec.	5	5
Resistivety, appl.visc. acc.SCH1.009	150	500	K-Ohm	300	350
Gloss, H60 acc. ISO2813	31.3	30	GU	5	5
Adhesion, Gitterschnitt acc.ISO2409	0	0	Gt	1	0
Layer thickness acc. ISO2808	35	30	µ	5	5
Sample stored d.d.	20.07.16				
Dryingcycle acc. SCH. 2.002		45'-60°C.			
Send Coa by email					
Controlled by	PAM		-		
Colour, visual appr. acc. ISO3668	acc.	good	-		
Sample received	yes	yes/no	-		
Appearance acc. SCH. 1.017	acc.	good	-		
Spray visc. DIN Cup 4 acc. ISO2431	17	16	Sec.	1	1
Flash-off time		10'-20°C.	Min.		
Substrate		degreased C-panel	-		
Hardener		H4P56 on vol. 57%			